



Chemcolor Sevnica d.o.o., Dolnje Brezovo 35, 8290 Sevnica, Identifikacijska številka za DDV: SI24218359
Tel.: +386 (0)7 81 63 550 / 81 60 100 Fax.: +386 (0)7 81 63 564 / 81 60 101 www.chemcolor.si

TECHNICAL INFORMATION

EXTRA HARD LAK

- PRODUCT DESCRIPTION:** **EXTRA HARD LAK DD** is a two-component Polyurethane parquet varnish. Component I is made up of desmofen based binder, component II is made of desmodur synthetic binders, which represents the hardener.
- FIELD OF USE:** It is suitable for lacquering of parquets, wood linings, joinery and furniture (tables, chairs, kitchen elements, office equipment...). It is resistant to wearing out. Its hardness (204 second/Koenig) enables to use **EXTRA HARD LAK DD** for very burdened surfaces (gymnasiums, offices...).
- SURFACE PREPARATION:** The floor must be smoothly whetted and dust free
- PAINT PREPARATION:** The two components should be well mixed (mixture ratio =1:1) and after 10 minutes applied on smoothly whetted surfaces with brush, roller or by spattering or casting over. Possible time to use the mixture is 6 hours. The first coating is diluted with 15-20% of **EXTRA HARD DILUENT**, further coatings with 10% of the diluent.
- APPLICATION:** with brush, roller or by spattering or casting over.
- THEORETICAL COVERAGE:** Theoretical application rate is 70-100g/m² - enough for one coating.
- NEXT LAYER:** Single coats can be whetted with fine sandpaper after 3 hours at 20°C.
- PHYSICAL PROPERTIES:**
- COLOR SHADES:** gloss, silky matt, semi-matt, and matt
- DENSITY:** 0,94 g/ml (20°C)
- SOLID VALUE:** 37 ± 2 % (mixture)
- VISCOSITY:** 25 s (F4 mm 20°C)
- HARDNESS:** 204s
- GLOSS:** 90,6% (gloss)
- THINNING AND CLEANING:** **EXTRA HARD DILUENT**
- PACKAGING:** SET 1, 3, 5.
- WAREHOUSING:** At least 12 months in originally sealed and undamaged packaging, in a dry and well ventilated place.
- NOTE:**

barve ki ščitijo vaš dom