



Chemcolor Sevnica d.o.o., Dolnje Brezovo 35, 8290 Sevnica, Identifikacijska številka za DDV: SI24218359  
Tel.: +386 (0)7 81 63 550 / 81 60 100 Fax.: +386 (0)7 81 63 564 / 81 60 101 www.chemcolor.si

## TECHNICAL INFORMATION

### HARD LAK

- PRODUCT DESCRIPTION:** **HARD LAK** is acid hardness parquet varnish and consists of two components. Component I is made up of high qualitative uric alkyd binders with not so much formaldehyde. Component II is an acid hardener.
- FIELD OF USE:** **HARD LAK** is suitable for lacquering of parquets, wood linings, joinery and furniture (tables, chairs, kitchen elements...). It is resistant to wearing out.
- SURFACE PREPARATION:** The floor must be smoothly whetted and dust free
- PAINT PREPARATION:** **One part** of component II should be poured into **ten parts** of component I. The mixture should be well mixed and after 10 minutes applied on the smoothly whetted surfaces. The mixture can be used 24 hours. The first coating is diluted with 15-20% of **HARD DILUENT**, further coatings with 10% of the diluent.
- APPLICATION:** with brush, roller or by spattering or casting over
- THEORETICAL COVERAGE:** Theoretical application rate is 70-100g/m<sup>2</sup> - enough for one coating.
- NEXT LAYER:** 2 hours. Single coats can be whetted with fine sandpaper after 2 hours at 20°C.
- PHYSICAL PROPERTIES:**
- COLOR SHADES:** gloss, silky matt, semi-matt, and matt
- DENSITY:** 0,97 g/ml (20°C)
- SOLID VALUE:** 43 ± 2 % (mixture)
- VISCOSITY:** 50 s (F4 mm 20°C)
- HARDNESS:** 198s
- GLOSS:** 90% (gloss)
- THINNING AND CLEANING:** **HARD DILUENT**
- PACKAGING:** SET: 1, 5, 10, 20.
- WAREHOUSING:** At least 12 months in originally sealed and undamaged packaging, in a dry and well ventilated place.
- NOTE:**

*barve ki ščitijo vaš dom*